ASIA PACIFIC INDUSTRY GROUP CO., LIMITED
Tel +0086-551-64687285
Email sales@boppfilmsales.com
www.boppfilmsales.com · www.apigcl.com

Asia Pacific BOPP Two Sides Heat Sealable -25micron

BOPP 薄膜 — 技术资料

Document No. 文件编号	Revision 版本	Issue date 签发日期	Document type 文件类型
APIG-RD-20180925141809-2026	**Rev. 2.0**	**2026-11-09**	**Technical Document / 技术资料**

1 • DOCUMENT INFORMATION 文档信息

Item 项目	Description 说明
Document type 文件类型	Technical Document / 技术资料
Subject 主题	Asia Pacific BOPP Two Sides Heat Sealable -25micron
Content basis 内容来源	Original technical document (archived) 原始技术资料（已归档）
Re-issue 重排发行	2026-11-09 · Rev. 2.0
Language 语言	Bilingual headings — English / 中文；正文依据原件转录

2 • TECHNICAL CONTENT 技术内容

Column 1	Nameofthe Product
Product	Bioriented Polipropilen Film
Common Name	BOPP25micron
Tech Name	Clear Polipropilen

Tables below are transcribed from the source; blank or illegible cells are shown as —.
以下表格依据原件转录；空白或不可辨单元格以 — 表示。

Name of the Product Bioriented Polipropilen Film Common Name BOPP 25 micron Tech Name Clear Polipropilen Description of the Product Bi-axially Oriented Polypropylene (BOPP) film, co-extruded, clear (transparent), with a good gloss and clarity, for high speed machines with fine sliding, smoothness and antistatic. Two side sealable and corona-treated in one face for printing and laminating by adhesion. For packaging Pasta; FDA compliant for contact with food.

以下内容提取自原始技术资料，并按本公司统一版式重排；数值与结论依据原件转录。

Product Identification and Handling 1. The product must be delivered in rolls; in plataforms and protected by walls; surrounded with strech polyethylene; there has to be no pollution agents present. 2. Each roll must have an identification label, containing: name of the supplier, type of product, lot, thickness, wide, and the face that has the treatment. 3. Each lot must have it’ s quality certificate. 4. The cores must have 6 inch diameter 5.

The external diameter of the rolls must be 730 mm maximum with 1 or 2 rolls per reinforced plataform. Technical Specifications Property Unit Max. Objective Min.

Method Criticity Unit weight g/m2 23.6 22.6 21.6 II-7.4-CJ-04 Critic Thikness micron 26.6 25 23.9 II-7.4-CJ-05 Critic m2/kg 46.1 44.2 42.3 II-7.4-CJ-04 Critic Resistance to Tension (break) DM/DT Lb/inch2 25091.5 51778.4 19142 38725.0 13246 27992.2 ASTM-D882 II-7.4-CJ-03 Great Resitance to Elongation DM/DT % 300 / 100 150 / 70 ASTM-D882 II-7.4-CJ-03 Great Superficial Tension or Treatment Level Dinas --- --- 38 ASTMD2578 II-7.4-CJ-01 Critic Dynamic coefficient of Friction PNT/PNT;

PNT/MET --- 0.45/0.31 0.30/ 0.21 0.15/0.11 ASTMD1894 II-8.2-CJ-02 Critic Temperature for Sealing initiation °C --- 120 --- II-8.2-CJ-18 Great Lb/inch2 --- --- 0.44 II-8.2-CJ-18 Great Flatness / Curvature mm 3 0 0 II-8.2-CJ-10 Critic Special Notes 1. Supplier must not change any property or specification without written autorization. 2. The specificatoin for this product cancel any past specifications. 3.

Not conforming with this data sheet will cause the rejection of the product

3 • NOTES 说明

地址 ADD.: No.3399, Luzhou Ave., Baohe Dist., Hefei, Anhui 230051, China | 安徽省合肥市包河区庐州大道3399号
传真 Fax: +0086-551-64683490 **营业执照注册号 Business License Reg. No.:** 91340100575703313N
海关注册编码 Customs Reg. Code: 3401961393

ASIA PACIFIC INDUSTRY GROUP CO., LIMITED
Tel +0086-551-64687285
Email sales@boppfilmsales.com
www.boppfilmsales.com · www.apigcl.com

Re-typeset content extract from the original technical document. Third-party issuing bodies, report numbers, signatures, seals, factory addresses, personal contacts and watermarks have been removed. Values are transcribed from the source and are indicative; the signed technical agreement governs any order.
本文件依据原始技术资料提取内容后重新排版，已移除第三方出证机构、报告编号、签名盖章、工厂地址、个人联系方式与水印。数值按原件转录，仅供参考，订单执行以正式技术协议为准。