ASIA PACIFIC INDUSTRY GROUP CO., LIMITED
Tel +0086-551-64687285
Email sales@boppfilmsales.com
www.boppfilmsales.com · www.apigcl.com

BOPP Capacitor Clear and Metallized Film - Technical Data

BOPP 薄膜 — 技术数据

Document No. 文件编号	Revision 版本	Issue date 签发日期	Document type 文件类型
APIG-TDS-BOPP-CAP-CM-2026	**Rev. 2.0**	**2026-11-09**	**Technical Data / 技术数据**

1 • DOCUMENT INFORMATION 文档信息

Item 项目	Description 说明
Document type 文件类型	Technical Data / 技术数据
Subject 主题	BOPP Capacitor Clear and Metallized Film - Technical Data
Content basis 内容来源	Original technical document (archived) 原始技术资料（已归档）
Re-issue 重排发行	2026-11-09 · Rev. 2.0
Language 语言	Bilingual headings — English / 中文；正文依据原件转录

2 • TECHNICAL CONTENT 技术内容

made by biaxial -orientation tente	Column 2	Column 3
high BDV and high mechanical strength The winded capacitors take on th		
0 .4 B +0 .1 V		
0 .3 C +0 .2 W		
0 .2 D +0 .3 X		

Tables below are transcribed from the source; blank or illegible cells are shown as —.
以下表格依据原件转录；空白或不可辨单元格以 — 表示。

01	E	+04	Y
0	L	+05	Z

d 3L 4E 5E 6E 7E 8D 9D 10D12D e t	Column 2	Column 3
TD % 50		
MD % 35 15min@120℃		

M-PP/S-PP ■Features By adopting the imported super high-purity capacitor-grade home-polypropylene resin, the film is made by biaxial-orientation tenter process.The film features excellent profile evenness, high BDV and high mechanical strength. The winded capacitors take on the characteristics of low dielectric dissipation and high insulation resistance. ■Application scope： M-PP：Mainly for metallized-film capacitor. S-PP：Mainly for foil-film capacitor.

■Technical Characteristics （typical value） Unit Typical Values Test conditions Tensile strengh MD MPa 140 Stretching speed:100% /min @23℃，50%r.h. .

TD MPa 250 Elongation at break MD % 100 TD % 50 Themal shrinkage MD % 3.5 15 min @ 120℃ TD % 1.0 Wetting tension [1] mN/m 38 Corona-treated Side Surface roughness μm 0.1 23℃ BDV X V/μm 550 at 23℃air Relative permittivity 2.2 50Hz or 1kHz @ 23℃ Volume resistivity Ω·m 5.0×1015 23℃ Dielectric dissipation factor(tan delta) 2×10-4 50Hz or 1kHz @23℃ * Reference Specification: IEC60674-2 * Values above are reference only , not for contracting.

* NOte:Uncorona-treated fot Type SPP ■Film thickness code： The nominal film thickness is indicated by its central value (integer value, e.g. 5,6.7 the first f igure after decimal or its codes. The nominal film thickness of this company is the Mechani- cal Method Value (MMV) under 10 layers testing. Number Letter Number Letter -0.4 B +0.1 V -0.3 C +0.2 W -0.2 D +0.3 X · -0.1 E +0.4 Y 0 L +0.5 Z Example： 8D indicates 7.8 um in MMV; thickness; 12X indicates 12.3 um .

ASIA PACIFIC INDUSTRY GROUP CO., LIMITED
Tel +0086-551-64687285
Email sales@boppfilmsales.com
www.boppfilmsales.com · www.apigcl.com

Remarks：The film of 3L.4E.5E.6E.7E.8D.9D and 10D etc. are recommended. 3L 4E 5E 6E 7E 8D 9D 10D 12D Thickness WMV μm 2.8 3.7 4.7 5.6 6.6 7.5 8.5 9.5 11.5 MMV μm 3.0 3.9 4.9 5.9 6.9 7.8 8.8 9.8 11.8 % ±3 Individual % ±9 ±7 ±5 Final film roll width mm 500， 620 Inner diameter mm 76.2， 152.4 Net weight kg 62，80 Note：Unusual specifications can be negotiated and specified additionally.

Capacitor Polypropylene Rough film type RPP/RRPP ■Features By adopting the imported super high-purity capacitor-grade homo-polypropylene resin, the rough film is produced by biaxial-orientation tenter process. The film features excellent physical and electrical properties, such as good profile evenness，high electric strength，low dielectric dissipation and good windability etc. The film can company with a good many kinds of capacitor impregnation oil well.

According to the authentication from National Power Capacitor Test Center, the product conforms to all the requirements of capacitor insulation materials. ■Application range: Mainly for power, electrothermal and other relevant kinds of high voltage capacitors designed as foil-film or foil-film & paper with oil-impregnation. ■Technical Characteristics （typical value） Unit Typical Values Test conditions Tensile strengh TD Mpa 140 Stretching speed 100mm/min @23℃，50%r.h.

TD Mpa 200 Elongation at break MD % 150 TD % 50 MD % 3.5 15 min @ 120℃ · Thermal shrinkage TD % 1.5 Space factor Average % 9.0（6～9μm） 10.0（10～18μm） 23℃ Limited % Max 15 Min 6 Surface roughness μm 0.25—0.65 23℃ BDV X(DC) V/μm 520 at 23℃air Relative permittivity 2.2 50Hz or 1kHz @23℃ Volume resistivity Ω.m 5.0×1015 23℃ Dielectric dissipation factor(tan delta) 2×10-4 50Hz or 1kHz @23℃ *Reference Specification: IEC60674-2 Values above are reference only , not for contracting.

3 • NOTES 说明

Re-typeset content extract from the original technical document. Third-party issuing bodies, report numbers, signatures, seals, factory addresses, personal contacts and watermarks have been removed. Values are transcribed from the source and are indicative; the signed technical agreement governs any order.
本文件依据原始技术资料提取内容后重新排版，已移除第三方出证机构、报告编号、签名盖章、工厂地址、个人联系方式与水印。数值按原件转录，仅供参考，订单执行以正式技术协议为准。