亞太工業集團
Asia Pacific Industry Group Co., Limited

ASIA PACIFIC INDUSTRY GROUP CO., LIMITED
Tel +0086-551-64687285
Email sales@boppfilmsales.com
www.boppfilmsales.com · www.apigcl.com

Clear Transparent CPP Film - Technical Data
CPP 薄膜 — 技术数据

Document No. 文件编号	Revision 版本	Issue date 签发日期	Document type 文件类型
APIG-TDS-CPP-CLR-2026	**Rev. 2.0**	**2026-11-09**	**Technical Data / 技术数据**

1 • DOCUMENT INFORMATION 文档信息

Item 项目	Description 说明
Document type 文件类型	Technical Data / 技术数据
Subject 主题	Clear Transparent CPP Film - Technical Data
Content basis 内容来源	Original technical document (archived) 原始技术资料（已归档）
Re-issue 重排发行	2026-11-09 · Rev. 2.0
Language 语言	Bilingual headings — English / 中文；正文依据原件转录

2 • TECHNICAL CONTENT 技术内容

TechnologydataofCPPFilm(Castpolypr	Column 2
Cleartransparent d ASIAPACIFICINDUSTRYGROUPCO LIMITED e ., Test Report	

Tables below are transcribed from the source; blank or illegible cells are shown as —.
以下表格依据原件转录；空白或不可辨单元格以 — 表示。

PROPERTIES		TEST METHOD	UNIT	TYPICAL DATAS
Thickness		ASTM D 2673	UM	20—90
Density		ASTM D 792	g/cm^3	0.90
Tensile strength	MD	ASTM D 882	MPa	65
	TD			35.2
Elongation at break	MD	ASTM D 882	MPa	551
	TD			646
C.O.F		ASTM D 1984	u/u	0.22
Surface tension		GB/T14216-93	Dyne	38
Heat seal temperature		SJ METHOD	℃	133
Haze		ASTM D 1003	%	2.6
Vapor permeation		ASTM D 1249	cc/m/24h	12
Oxygen permeation		ASTM 3985	cc/m/24h	2.6

Product / packing view 1 产品 / 包装实拍 1

Technology data of CPP Film (Cast polypropylene film) Clear transparent Test Report HS code Film Type CPP film for bread bag Film spec. 25-40mic Sampling Site warehouse Batch No.
以下内容提取自原始技术资料，并按本公司统一版式重排；数值与结论依据原件转录。

2 Test Date 2018.12.25 Film Grade A++ Test Standart QB/T 1125-2000 Test Items Target Date LCPP-1 (40mic Asia market) 30mic for Canada area 25mic for Russia area 1.Width Deviation (mm) 890+4 726 1029 920 2.Thick.Deviation(%) 20±10% 40±3% 30±3% 25±4% 3.Appreanc e Perforation,scra tch,Wrinkles,fis h eye Not allowed Qualified 4.Tensile Str ength (Mpa) MD ≥35 40.5 46.3 51.4 TD ≥25 29 33.6 31.8 5.Blongatio n at Break MD ≥350 489 451 485 TD ≥450 574 696 751 6.Haze(%) ≤5 2.9 2.1 2.7 7.COF (non-treate d side) Uk ≤0.35 0.18 0.14 0.14 Us ≤0.35 0.16 0.14 0.12 8.Wetting Tension (mN/m) ≥38 38 38 Qualified these 3 type CPP film are FYI only, we can customize what you want exactly.

TECHNOLOGY DATA (Physical Properties) Application: CCP films are used for food and medicine flexible packaging, As well as dry-compounded with BOPET、BOPP、BOPA etc., Use for food and medicine flexible packaging. Characters: □ Excellent clarity □ Good for protection against the moisture □ Fitting of C.O.F. □ Excellent printing and compounding □ Low heat seal temperature Typical values： CPP FILM ·

ASIA PACIFIC INDUSTRY GROUP CO., LIMITED
Tel +0086-551-64687285
Email sales@boppfilmsales.com
www.boppfilmsales.com · www.apigcl.com

3 • NOTES 说明

Re-typeset content extract from the original technical document. Third-party issuing bodies, report numbers, signatures, seals, factory addresses, personal contacts and watermarks have been removed. Values are transcribed from the source and are indicative; the signed technical agreement governs any order.
本文件依据原始技术资料提取内容后重新排版，已移除第三方出证机构、报告编号、签名盖章、工厂地址、个人联系方式与水印。数值按原件转录，仅供参考，订单执行以正式技术协议为准。