ASIA PACIFIC INDUSTRY GROUP CO., LIMITED
Tel +0086-551-64687285
Email sales@boppfilmsales.com
www.boppfilmsales.com · www.apigcl.com

Water-Based Pressure-Sensitive Adhesive for Films - Technical Data

胶粘剂 — 技术数据

Document No. 文件编号	Revision 版本	Issue date 签发日期	Document type 文件类型
APIG-TDS-GLUE-WB-2026	**Rev. 2.0**	**2026-11-09**	**Technical Data / 技术数据**

1 • DOCUMENT INFORMATION 文档信息

Item 项目	Description 说明
Document type 文件类型	Technical Data / 技术数据
Subject 主题	Water-Based Pressure-Sensitive Adhesive for Films - Technical Data
Content basis 内容来源	Original technical document (archived) 原始技术资料（已归档）
Re-issue 重排发行	2026-11-09 · Rev. 2.0
Language 语言	Bilingual headings — English / 中文；正文依据原件转录

2 • TECHNICAL CONTENT 技术内容

离子性 阴离子 改性苯乙烯-丙烯酸酯乳液共聚物 水性自交联苯乙烯-丙烯酸酯共聚乳液，具有粘结力强、流动性好、涂布性能优异等特点，适用于PP 透明、PP 白色、PP 银色、PP 合成纸、PP 珠 光等；PE 透明、PE 白色、PE 亮银等；PET 透明、PET 银色、PET 亮 白、PET 哑白, PVC 透明、 PVC 白色、PVC 银色等离型塑料膜标签及广告材料的粘合。
□无毒、环保 □优异的耐候性 □涂布性能优异，适合转移涂布 □极长时间的持粘力，极佳平衡的初粘力和终粘力 外观 乳白色液体 pH 7.0-8.0 固含量 54±1% 粘度(25℃) 200-300cP □适用于PP、PE、PET、PVC 等膜标签及广告材料的粘合 □200 公斤/塑料桶 □产品应贮存在密闭容器内，避免冷冻及高温，建议正常贮存温度 在5℃~35℃，贮存期自包装之日起为6个月 □可按非危险品运输 · Acrylic ester aqueous dispersion SA-233 is an adhesive specially designed for reverse gravure coaters, for the production of general purpose filmic labels (PP, PE, PVC, and PET etc.) or other pressure sensitive articles.

以下内容提取自原始技术资料，并按本公司统一版式重排；数值与结论依据原件转录。

□Non-yellowing □Repositionability □Excellent balance of tack and shear □Ideal for usein general clear and/or coloured polyolefinic film labels Milky white liquid pH 6.5-8.5 Solid content 50±1% Type of emulsion Anionic Viscosity (25℃) 100-200mPa·s Density (20℃) 1.02 g/cm3 Surface of the film Tacky, clear □General purpose polyolefinic film labels □Other pressure sensitive articles etc.

□Available in 200 kg/ barrel or 1000 kg/ barrel (IBC) □Store products in tightly closed original containers at5-35℃ □Shelf life: 6-9 months from delivery date □According to non-dangerous goods transport ·

3 • NOTES 说明

Re-typeset content extract from the original technical document. Third-party issuing bodies, report numbers, signatures, seals, factory addresses, personal contacts and watermarks have been removed. Values are transcribed from the source and are indicative; the signed technical agreement governs any order.
本文件依据原始技术资料提取内容后重新排版，已移除第三方出证机构、报告编号、签名盖章、工厂地址、个人联系方式与水印。数值按原件转录，仅供参考，订单执行以正式技术协议为准。